

MoS₂ Bonded Coating Spray TC 46



Product description

MoS₂ Bonded Coating Spray TC 46 is based on very fine quality of MoS₂ used as dry lubricant for sliding surfaces operating in dirty or dusty conditions for temperature up to + 450°C.

Applications

It gives fully dry, permanent and high load carrying lubrication. Film is totally resistant to radiation and water .

Advantages

Dry film lubricant designed to provide life time lubrication for lightly loaded or slow moving, highly loaded sliding surfaces • It forms a bonded film of molybdenum disulphide which reduces friction and wear and guards against seizure, pickup and galling.

Handling instructions.

Shake the can well before use, till the movement of steel ball inside the can is audible. Keep away from open flame & heat. Do not store above 50°C .Contents under pressure. Highly flammable material. Check for compatibility before use. Use a brush to remove hard deposits from the chain. Refer MSDS for more information about safe use, physical & health hazards.

Technical Properties

Parameter	Value	Unit	Standard
Appearance	Grey dry film		
Density	~ 0.90	g/cc	
Film thickness	15	Microns	
Drying time	~ 10	Minutes	
Curing time	~ 30	Minutes	
Flash point	< 0	°C	ASTM D 566

Limited warranty: The information & data contained in this catalogue is accurate to the best of our knowledge or is obtained from sources, tests or experience believed by us to be accurate. User is responsible for determining whether this is fit for a particular application. We make no representation of any kind & data mentioned herein is offered without any warranty. TriboCor's sole warranty is that the product will meet the specs at the time of shipment. All data is subject of change without prior notice.

V1120

TriboCor Technologies Private Limited,

57/3, Opp NKCA Pharmacy, Srirampura, Mysore - 570008, India.

Customer Care : 0821 2361110, +91 934 258 9006, +91 984 409 2722

E-mail : tribocor@gmail.com Web : www.tribocor.co.in

TriboCor[®]
High Performance Aerosol